







**Publisher:** NOVO-TECH Trading GmbH & Co. KG Siemensstraße 31, D-06449 Aschersleben, Germany

**Distribution:** Holz-Speckmann GmbH & Co. KG Weststraße 35, D-33790 Halle/Westf., Germany Tel.: +49 (0) 5201-189-330 · Fax: +49 (0) 5201-189-312 www.megawood.com · distribution@megawood.de

Design/layout: NOVO-TECH Trading GmbH & Co. KG

**Picture credits:** Christian Wolf, Thomas Gasparini Harald Eichler

### **Table of Contents**

Table of Contents	2
List of items	3
Care instructions	13
Care tips – timeline	15
Colour development	16
Association of the German Wood-Based Panel Industry	17
Impregnation	18
Certificate indoor protect	19
Quality standards megawood® floorboards	20
Technical Information	21
General technical approval	22
Fraunhofer Institut for Mechanics of Materials	24
Test report - mould fungi	28
Safety information	32
Forms of delivery and packing units for decking	34
Certificate Cradle to Cradle	47
Certificate PEFC	48
Certificate Seal of Quality	50
Certificate solid boards - exemplary	51
Anti-slip properties test reports	52
Certificate classification of fire behavior	56
Marker for APP	60

Subject to change. Colours and graphics may differ due to printing processes. Date: February 2021/english

megawood® decking					
Art. no.	Profile	Art. name	Colour	Length cm	H x W mm
MWDE021145VG420-600 MWDE021145VS420-600 MWDE021145IN420-600 MWDE021145SG420-600 MWDE021145L0420-600		DELTA DELTA DELTA DELTA DELTA DELTA	varia grey varia chocolate black ingwer sel gris lorbeer	420,480,600 420,480,600 420,480,600 420,480,600 420,480,600	21×145 21×145 21×145 21×145 21×145
NOVO070-300-600FE NOVO071-300-600FE NOVO073-300-600FE NOVO075-300-600FE NOVO076-300-600FE		CLASSIC CLASSIC CLASSIC CLASSIC CLASSIC	natural brown basalt grey nut brown slate grey lava brown	300,360,420,480,540,600 300,360,420,480,540,600 300,360,420,480,540,600 300,360,420,480,540,600 300,360,420,480,540,600	21x145 21x145 21x145 21x145 21x145
NOVO090-300-600FE NOVO091-300-600FE NOVO093-300-600FE NOVO094-300-600FE NOVO095-300-600FE		CLASSIC Jumbo CLASSIC Jumbo CLASSIC Jumbo CLASSIC Jumbo CLASSIC Jumbo	natural brown basalt grey nut brown slate grey lava brown	420,480,600 420,480,600 420,480,600 420,480,600	21x242 21x242 21x242 21x242 21x242
MWCV021195VB420-600 MWCV021195VG420-600 MWCV021195VS420-600		CLASSIC Varia CLASSIC Varia CLASSIC Varia	varia brown varia grey varia chocolate black	420,480,600 420,480,600 420,480,600	21x195 21x195 21x195
PS001-300-600FE PS002-300-600FE		SIGNUM SIGNUM	muskat tonka	360, 420, 480, 540, 600 360, 420, 480, 540, 600	21 x 145 21 x 145
PJS090-300-600FE PJS091-300-600FE		SIGNUM Jumbo SIGNUM Jumbo	muskat tonka	360,420,480,540,600 360,420,480,540,600	21×242 21×242
PD001-300-600FE PD002-300-600FE PD003-300-600FE		PREMIUM PREMIUM PREMIUM	natural brown basalt grey nut brown	420,480,600 420,480,600 420,480,600	21 x 145 21 x 145 21 x 145
PJ090-300-600FE PJ091-300-600FE PJ093-300-600FE		PREMIUM Jumbo PREMIUM Jumbo (abZ)* PREMIUM Jumbo (abZ)*	natural brown basalt grey nut brown	420,480,600 420,480,600 420,480,600	21x242 21x242 21x242
PD004-300-600FE PD005-300-600FE		PREMIUM PLUS PREMIUM PLUS	slate grey lava brown	420,480,600 420,480,600	21×145 21×145
PJ094-300-600FE PJ095-300-600FE		PREMIUM PLUS Jumbo PREMIUM PLUS Jumbo	slate grey lava brown	420,480,600 420,480,600	21x242 21x242
DY110-360-600FE DY120-360-600FE DY130-420-600FE DY140-420-600FE DY150-420-600FE		DYNUM DYNUM DYNUM DYNUM DYNUM	cardamom nigella ingwer sel gris lorbeer	420,480,600 420,480,600 420,480,600 420,480,600 420,480,600	21x242 21x242 21x242 21x242 21x242
DY210-360-600FE DY220-360-600FE DY230-420-600FE DY240-420-600FE DY250-420-600FE		DYNUM (abZ)* DYNUM (abZ)* DYNUM DYNUM DYNUM	cardamom nigella ingwer sel gris lorbeer	420,480,600 420,480,600 420,480,600 420,480,600 420,480,600	25x293 25x293 25x293 25x293 25x293

<sup>\* (</sup>abZ) General Building Approval.

megawood® sub construction				
Art. no.	Profile	Art. name	Colour	LxWxH mm
NOVO004-360FE		Sub construction 40x60mm	grey	3,600 x 60 x 40
MWUK080060GR400	<b>A</b>	Sub construction 80x60mm	grey	4,000×60×80
KP010-360FE		Connector for sub construction 40x60 mm and sub construction 80x60 mm	grey	3,600x76x28

megawood® accessories sub construction				
Art. no.	Profile	Art. name	Colour	LxWxH mm
NOV0007-28		Sub construction fixing screws 92 mm TX 30	galvanized	92×7.5
NOV0007-30		Sub construction fixing screws 132 mm TX 30	galvanized	132 x 7.5
NOVO015-12	0	Self-adhesive retaining band 10 m/roll	black	10 x 12
NOVO017-21	14	Groove bridge, 20 pcs. for construction beams	V2A	55×10×8

megawood® FIX STEP system					
Art. no.	Profile	Art. name	Colour	LxWxH mm	
NOV0017-02	-	Edge plate DUO for double construction beams $40 \times 60  \text{mm}$ and $80 \times 60  \text{mm}$	black	280×252×71	
NOVO017-04	No. of London	Edge fixture DUO for double construction beams $40 \times 60  \text{mm}$ and $80 \times 60  \text{mm}$	black	250×60×55	
NOVO017-01		Standard plate for simple construction beams $40 \times 60  \text{mm}$ and $80 \times 60  \text{mm}$	black	270×180×71	
NOV0017-03	1	Edge fixture standard for simple construction beams 40 x 60 mm and 80 x 60 mm	black	116×60×55	

megawood® VARIO FIX					
Art. no.	Profile	Art. name	Colour	LxWxH mm	
MWVFUK100000SW	2	VARIO FIX I (40 - 143); with fixture for sub construction 40 x 60 mm and sub construction 80 x 60 mm	black	295×148×70	
MWVFUK200000SW	-4	VARIO FIX II (44 - 242) with fixture for sub construction 40 x 60 mm and sub construction 80 x 60 mm	black	295×148×70	

megawood® FIX STEP and VARIO FIX					
Art. no.	Profile	Art. name	Colour	LxWxH mm	
NOVO017-05	*	Attachment for elevated construction	black	79×58×63	
NOV0017-07	4	Comfort pad for elevated construction	black	79×58×20	
NOVO017-08		Assembly clip 10 pcs., without screws	V2A blackened	78×40×0	
NOVO017-17 NOVO017-18 NOVO017-19	=	Rubber pad Rubber pad Rubber pad	black black black	300×300×3 300×300×5 300×300×10	
NOVO017-20	9	Perforated tape 10 m roll	black	10,000×14×2	
NOVO017-23	00-0	Screws for perforated tape M6 x 16 mm + washer + nut, 10 pieces	V2A	M6x16	

megawood® accessories profiles and strips				
Art. no.	Profile	Art. name	Colour	LxWxH mm
NOVO017-14 NOVO017-15		Groove strip, 25 m/roll Groove strip, 100 m/roll	black black	21x12 21x12
MWNL00000007SW MWNL00000008SW		Groove strip P5, 25 m/roll Groove strip P5, 100 m/roll	black black	25,000 x 11 x 5.5 100,000 x 11 x 5.5
MWLG105021ED200		Ventilation grilles Fastening: screw M6 x 40 mm	V2A	2,000 x 105 x 21
NOVO008-401 NOVO008-408	4	25 mm House connection profile, aluminium 25 mm House connection profile, aluminium	silver anthrazit	4,000 x 45 x 59 4,000 x 45 x 59
NOVO008-402 NOVO008-403 NOVO008-404	4	21 mm House connection profile, aluminium 21 mm House connection profile, aluminium 21 mm House connection profile, aluminium	bronze silver anthrazit	4,000 x 45 x 55 4,000 x 45 x 55 4,000 x 45 x 55
NOVO008-405 NOVO008-406 NOVO008-407		Miter profile, aluminium Miter profile, aluminium Miter profile, aluminium	bronze silver anthrazit	4,000 x 50 x 25 4,000 x 50 x 25 4,000 x 50 x 25
NOV0007-21	0	Sealing tape for miter profile 20 mm, 13 m/roll		13,000×20×2

megawood® accessories decking assembly				
Art. no.	Profile	Art. name	Colour	LxWxH mm
NOVO017-0110 NOVO017-0111		Locking clamp, one-piece, 50 pcs./pack Locking clamp, one-piece, 250 pcs./pack	V2A blackened	66 x 24 x 27 66 x 24 x 27
NOV0007-0120		Locking clamp edge, one-piece, 25 pcs./pack	V2A blackened	66×18×27
NOVO007-011 NOVO007-025 NOVO007-050 NOVO007-012	BB	Clip, 50 pcs./pack Clip, 250 pcs./pack Clip, 500 pcs./pack Edge clip, 25 pcs./pack	V2A V2A V2A black	35×24×7.7 35×24×7.7 35×24×7.7 35×21×7.7
NOVO016-01 NOVO016-11 NOVO016-21	2	Rubber pad Rubber pad Rubber pad	black black black	100×60×20 100×60×10 100×60×3
NOVO007-013		Distance keeper, Mounting aid for decking	grey	60×16×20
NOVO007-014	VE-	Zammer  Mounting aid for one-piece locking clamp		275×15×65
MWZUNL000009ED	7	Rolli, additional part for Zammer Mounting aid for groove strip P5		47×47×70
NOVO017-22	30	Screw M8 x 80 mm + washer + nut, 10 pieces	V2A	M8x80
MWBFRP000014ED	-	Screw M8 x 40 mm, 10 pieces/pack	V2A	M8 x 40
MWBFFP000011ED		Screw M6 x 40 mm, 10 pieces/pack	V2A	M6 x 40
NOVO007-05	_	Screw set 4 x 35 mm, 25 pieces/pack	V2A	4 x 35 mm
MWDHUK000006SW	1	Distanz Fix Spacers for heading joints	V2A blackened	162×54×20
MWBFFP000010SW	1	Arretier Fix for a height locking of the butt joints	V2A blackened	70×25×5

megawood® cleaning & accessories				
Art. no.	Profile	Art. name	Colour	LxWxH mm
MWDESP2UG000WE		Scouring powder , Quantity: 2000 g		85 x 138 x 350
MWDESR000000HO		Scrubbing brush		200 x 50 x 45
MWDEST000000HO		Scrubbing shaft; incl. holder and 2 wing screws		Stiel Ø32 1630 x 115 x 32

megawood® accessories impregnation for indoor use					
Art. no.	Profile	Art. name	Colour	LxWxH mm	
NOVO016-113		megawood Indoor Protect 750 ml can		Ø10×120	
NOVO016-112	E 19	megawood Indoor Protect 2.5 L can		Ø14×190	

### megalite LED lighting system

megawood® accessor	ies decking me	galite LED lighting system		
Art. no.	Profile	Art. name	Colour	LxWxH mm
		LED-Linear light horizontal, 3,600 mm,		
MWLL000021NW360		27 W / 27lm/W = 729lm per Linear light	neutral white	3,600 x 62 x 21
MM/// 1 0000021 NM/// 00		LED-Linear light horizontal, 4,800 mm,	مغنوان المسغرية	/ 200 v C2 v 21
MWLL000021NW480	/	36 W / 27lm/W = 972lm per Linear light LED-Linear light horizontal, 6,000 mm,	neutral white	4,800 x 62 x 21
MWLL000021NW600		45 W / 27lm/W = 1215lm per Linear light	neutral white	6,000 x 62 x 21
		LED-Linear light vertical, 3,600 mm,		
MWLL0000SRNW360	1	27W / 27lm/W = 729lm per Linear light	neutral white	3,600 x 62 x 21
MWLL0000SRNW480		LED-Linear light vertical, 4,800 mm, 36 W / 27lm/W = 972lm per Linear light	neutral white	/, 900 v 62 v 21
MWLLOOOOSKNW480		LED-Linear light vertical, 6,000 mm,	neutrat white	4,800×62×21
MWLL0000SRNW600		45 W / 27lm/W = 1215lm per Linear light	neutral white	6,000 x 62 x 21
	1	LED-Spot Mini 34 mm, IP 67 24 V DC		
MWSP000000NW034		(0,25 W/9 LED / 40lm/W = 10lm per Spot)	neutral white	Ø34
	59	LED-Spot Maxi, IP 67 24V DC		
MWSP00000NW060		(0.5  W/18  LED  / 56 lm/W = 28 lm per Spot)	neutral white	Ø 60
MWNG0000040W24V	-	Power supply electronic ballast 24V DC IP 67, 40 W		270 x 30 x 17
MWNG000000024V	~	Power supply electronic ballast 24V DC IP 67, 150 W		190 x 62 x 36.5
	100	Repeater		
MWRP000000024V		24V IP 67, max. 72 W		160 x 79 x 55
MWFS000000024V	-1000	Remote control set 24V IP 67, incl. remote, control, transmission capacity max. 72 W		200 x 79 x 55 184 x 28 x 21.5
MWVL000000SW100		Extension cables IP 68, 1,000 mm	black/blue	1,000 mm
MWVL000000SW300	-	Extension cables IP 68, 3,000 mm	black/blue	3,000 mm
MWVL000000SW600		Extension cables IP 68, 6,000 mm	black/blue	6,000 mm
MWVT000000SW002	4	Distributor 2-fold, IP 68	black/blue	75 x 17.5 x 40
MWVT000000SW004	Liber	Distributor 4-fold, IP 68	black/blue	145 x 17.5 x 40
MWLM000000NW360		LED bulb, 3,600 mm,	noutral white	2 E E E mm
MWLM000000NW360		(27 W / 27lm/W = 729lm per bulb) LED bulb, 4,800 mm,	neutral white	3,565 mm
MWLM000000NW480		(36 W / 27lm/W = 972lm per bulb)	neutral white	4,765 mm
	F	LED bulb, 6,000 mm,		
MWLM000000NW600	1	(45 W / 27lm/W = 1215lm pro per bulb)	neutral white	5.965 mm
MWAP000021MW360		Cover profile horizontal, 3,600 mm	matte white	3,600 x 62 x 10
MWAP000021MW480 MWAP000021MW600		Cover profile horizontal, 4,800 mm  Cover profile horizontal, 6,000 mm	matte white matte white	4,800 x 62 x 10
MWAP000021MW800		Cover profile vertical, 3,600 mm	matte white	6,000 x 62 x 10
MWAPOOOSRMW380		Cover profile vertical, 3,600 mm	matte white	3,600 x 62 x 21 4,800 x 62 x 21
MWAP0000SRMW600		Cover profile vertical, 6,000 mm	matte white	6,000 x 62 x 21
MWPR000000AL360	1	Aluminium profile, 3,570 mm	aluminium	3,570 x 58 x 21
MWPR000000AL480		Aluminium profile, 4,770 mm	aluminium	4,770 x 58 x 21
MWPR000000AL600		Aluminium profile, 5,970 mm	aluminium	5.970 x 58 x 21
MMEKOOOOOALOOO	-25	End caps for Linear light	ali mai air mi	15 , 50 , 17
MWEK000000AL000		2 pieces + 4 screws	aluminium	15 x 58 x 17

# LIMES fencing system

megawood® LIMES f	encing system				
Art. no.	Profile	Art. name	Colour	Length cm	H x W mm
MWPR090090LA220 MWPR090090SC220 MWPR090090LA270 MWPR090090SC270		Circular posts Circular posts Circular posts Circular posts	lava brown slate grey lava brown slate grey	220 220 270 270	Ø90 Ø90 Ø90 Ø90
MWP8090090LA220 MWP8090090SC220 MWP8090090LA270 MWP8090090SC270		Octagonal posts Octagonal posts Octagonal posts Octagonal posts	lava brown slate grey lava brown slate grey	220 220 270 270	90×90 90×90 90×90 90×90
MWP4090090LA220 MWP4090090SC220 MWP4090090LA270 MWP4090090SC270		Square posts Square posts Square posts Square posts	lava brown slate grey lava brown slate grey	220 220 270 270	90×90 90×90 90×90 90×90
MWPF060090LA220 MWPF060090SC220 MWPF060090LA270 MWPF060090SC270		Oval posts Oval posts Oval posts Oval posts	lava brown slate grey lava brown slate grey	220 220 270 270	60 x 90 60 x 90 60 x 90 60 x 90
MWPW270035IN160 MWPW270035SG160 MWPW270035L0160 MWPW270035IN181 MWPW270035SG181 MWPW270035L0181 MWPW270035IN210 MWPW270035SG210 MWPW270035L0210		Panel Augusta (wavy)	ingwer sel gris lorbeer ingwer sel gris lorbeer ingwer sel gris	160,2 160,2 160,2 180,5 180,5 180,5 210 210	270 x 35 x 6 270 x 35 x 6
MWPG239006IN158 MWPG239006SG158 MWPG239006L0158 MWPG239006IN210 MWPG239006SG210 MWPG239006L0210		Panel Colonia (smooth)	ingwer sel gris lorbeer ingwer sel gris lorbeer	158,4 158,4 158,4 210 210 210	239 x 6 239 x 6 239 x 6 239 x 6 239 x 6 239 x 6
MWKB040112LA179 MWKB040112SC179		Bar Bar	lava brown slate grey	178,6 178,6	40 x 112 40 x 112
MWPF060090LA179 MWPF060090SC179		Oval bar Oval bar	lava brown slate grey	178,6 178,6	60x90 60x90
MWBF038030LA157 MWBF038030SC157		H-shaped profile bar (8 units) H-shaped profile bar (8 units)	lava brown slate grey	156,6 156,6	38 x 30 38 x 30
MWBF038030LA179 MWBF038030SC179 MWBF038030LA190 MWBF038030SC190		H-shaped profile bar H-shaped profile bar H-shaped profile bar H-shaped profile bar	lava brown slate grey lava brown slate grey	178,6 178,6 190 190	38 x 30 38 x 30 38 x 30 38 x 30
MWEW035177IN185 MWEW035177SG185 MWEW035177L0185		Fence set with stainless steel bar, comprising of: 7 panels AUGUSTA (wavy) 1,805 mm 2 stainless steel bars incl. post fastening 1,773 mm 1 insert bar for stainless steel bar 1,770 mm 1 accessories set for stainless steel bar	ingwer sel gris lorbeer	185 185 185	1,805 x 42 1,805 x 42 1,805 x 42

# LIMES fencing system & accessories

megawood® LIMES fencing system					
Art. no.	Profile	Art. name	Colour	Length cm	H x B mm
MWPH235025VG193 MWPH235025VS193 MWPH235025IN193		Panel Valeria Panel Valeria Panel Valeria	varia grey varia chocolate black ingwer	193 193 193	25 x 235 25 x 235 25 x 235
MWPN100100VG220 MWPN100100VS220 MWPN100100IN220 MWPN100100VG270 MWPN100100VS270 MWPN100100IN270		Post for panel Valeria	varia grey varia chocolate black ingwer varia grey varia chocolate black ingwer	220 220 220 270 270 270	100×100 100×100 100×100 100×100 100×100
MWEL006034VG220 MWEL006034VS220 MWEL006034IN220	/	Insertion bar for Post Valeria Insertion bar for Post Valeria Insertion bar for Post Valeria	varia grey varia chocolate black ingwer	220 220 220	6x34 6x34 6x34
MWZUPF000001ED	0	Post cap for Post Valeria	V2A		Ø105

megawood® fencing system accessories					
Art. no.	Profile	Art. name	Colour	LxWxH mm	
MWBFKB000001SW	4	Bar connectors; incl M6 x 30 mm screws; 4 units	blackened	85×35×11	
MWBFPA000002ED	56	Panel holder; stainless steel, 16 units	stainless steel	42x15x12	
MWBFPF000003ED	222	Base plate; incl. 4 units M8 x 80 mm screws	galvanized	140 x 120 x 10	
MWBFHP000004ED	/	Pin; 10 units, 6 x 40 mm	stainless steel	105×96×57	
MWBFHP000005ED	/	Internal hexagonal screw for H-shaped profile bar incl. bit, 16 units	stainless steel	M4×40	
MWRI042060ED177		Stainless steel bar	stainless steel	1,773 x 60 x 42	
MWEL019023GR177	/	Insert bar for stainless steel bar	grey	1,770×23×19	
MWBFRI000012ED	1	Assessories set for stainless steel bar incl. post fastening (4 units + accessories)	stainless steel	95x45x50	

# Construction wood system

megawood® construction wood system					
Art. no.	Profile	Art. name	Colour	Länge cm	H x W mm
KP004-360GRFE		Construction plank	basalt grey	360	40×112
KP005-360NUFE		Construction plank	nut brown	360	40 x 112
KP006-360BRFE		Construction plank	natural brown	360	40 x 112
KP009-360LBFE	1.0	Construction plank	lava brown	360	40 x 112
KP011-360SGFE	A	Construction plank	slate grey	360	40 x 112
MWKB040112IN360		Construction plank	ingwer	360	40 x 112
MWKB040112SG360	1	Construction plank	sel gris	360	40 x 112
MWKB040112L0360		Construction plank	lorbeer	360	40 x 112
MWKB040112MU360		Construction plank	muskat	360	40 x 112
MWKB040112T0360		Construction plank	tonka	360	40 x 112
KP012-420FE		Construction plank	natural brown	420	40 x 145
KP013-420FE		Construction plank	basalt grey	420	40 x 145
KP014-420FE		Construction plank	nut brown	420	40 x 145
KP015-420FE		Construction plank	lava brown	420	40 x 145
KP016-420FE		Construction plank	slate grey	420	40 x 145
MWKB040145IN420		Construction plank	ingwer	420	40 x 145
MWKB040145SG420		Construction plank	sel gris	420	40 x 145
MWKB040145L0420		Construction plank	lorbeer	420	40 x 145
MWKB040145MU420		Construction plank	muskat	420	40 x 145
MWKB040145T0420		Construction plank	tonka	420	40 x 145
MWKR090090LA360	A	Circular construction wood	lava brown	360	Ø 90
MWKR090090SC360		Circular construction wood	slate grey	360	Ø 90
MWK8090090LA360	A	Octagonal construction wood	lava brown	360	90 x 90
MWK8090090SC360		Octagonal construction wood	slate grey	360	90×90
MWK4090090LA360	A	Square construction wood	lava brown	360	90 x 90
MWK4090090SC360		Square construction wood	slate grey	360	90 x 90
MWK0090090LA360	A	Oval construction wood	lava brown	360	60 x 90
MWK0090090SC360		Oval construction wood	slate grey	360	60 x 90
MWRP021081NB420		Construction wood Rhombus	natural brown	420	20.5 x 81
MWRP021081NU420		Construction wood Rhombus	nut brown	420	20.5 x 81
MWRP021081VG420		Construction wood Rhombus	varia grey	420	20.5 x 81
MWRP021081VB420		Construction wood Rhombus	varia brown	420	20.5 x 81
MWRP021081VS420		Construction wood Rhombus	varia chocolate black	420	20.5 x 81
MWRP021081IN420		Construction wood Rhombus	ingwer	420	20.5 x 81
MWRP021081SG420		Construction wood Rhombus	sel gris	420	20.5 x 81
MWRP021081L0420		Construction wood Rhombus	lorbeer	420	20.5 x 81

megawood® accessories construction wood system					
Art. no.	Profile	Art. name	Colour	LxWxH mm	
MWBFRP000001ED	13	Clamp for construction wood Rhombus 30 pcs./pack	stainless steel	40×83.6×15	
MWBFRP000002SW	A STAN	Clamp for construction wood Rhombus 30 pcs./pack	stainless steel blackened	40×83.6×15	

# Construction wood system

megawood® bench				
Art. no.	Profile	Art. name	Colour	LxWxH mm
FS020-205		Bench	natural brown	1,800 x 960 x 690
FS020-203		Bench	basalt grey	1,800 x 960 x 690
FS020-202		Bench	nut brown	1,800 x 960 x 690
FS020-206	-	Bench	lava brown	1,800 x 960 x 690
FS020-207	1	Bench	slate grey	1,800 x 960 x 690
FS020-208	A	Bench	ingwer	1,800 x 960 x 690
FS020-209	P	Bench	sel gris	1,800 x 960 x 690
FS020-210		Bench	lorbeer	1,800 x 960 x 690
FS020-211		Bench	muskat	1,800 x 960 x 690
FS020-212		Bench	tonka	1,800 x 960 x 690

megawood® plant container				
Art. no.	Profile	Art. name	Colour	LxWxH mm
MWPK110110LA081		Plant container	lava brown	1,000 x 1,000 x 810
MWPK110110SC081		Plant container	slate grey	1,000 x 1,000 x 810

megawood® sandpits				
Art. no.	Profile	Art. name	Colour	LxWxH mm
MWSK120120LA030	0	Sandpits 1x6-eck	lava brown	1,200 x 1,200 x 300
MWSK120120SC030	-	Sandpits 1 x 6-eck	slate grey	1,200 x 1,200 x 300
MWSK120210LA030	0	Sandpits 2 x 6-eck	lava brown	1,200 x 2,100 x 300
MWSK120210SC030	0	Sandpits 2 x 6-eck	slate grey	1,200 x 2,100 x 300
MWSK210210LA030	-	Sandpits 3 x 6-eck	lava brown	2,100 x 2,100 x 300
MWSK210210SC030	~	Sandpits 3 x 6-eck	slate grey	2,100 x 2,100 x 300

megawood® door					
Art. no.	Profile	Art. name	Colour	LxWxH mm	
MWTR004102LA185		Door, no filling, incl. fittings	lava brown	1,020 x 40 x 1,850	
MWTR004102SC185		Door, no filling, incl. fittings	slate grey	1,020 x 40 x 1,850	

megawood® frame					
Art. no.	Profile	Art. name	Colour	LxWxH mm	
MWZR040112LA270 MWZR040112SC270		Frame, comprising of construction planks	lava brown	1,120 x 145 x 1,850	
MWZR040112SC270		Frame, comprising of construction planks	slate grey	1,120 x 145 x 1,850	

# Assembly

megawood® LIMES standard section assembly					
Art. no.	Profile	Art. name	Colour	LxWxH mm	
		LIMES standard section assembly			
		Consists of: Assembly of the bar connectors.			
MWKONF0001		Drilling of the holes for the panel holders.			

megawood® LIMES adapted section assembly					
Art. no.	Profile	Art. name	Colour	LxWxH mm	
	H	LIMES adapted section assembly Consists of: Reduction in the width/height of the elements and assembly of the bar connectors.			
MWKONF0002		Drilling of the holes for the panel holders.			

megawood® LIMES diagonal section assembly						
Art. no.	Profile	Art. name	Colour	LxWxH mm		
MWKONF0003		LIMES diagonal section assembly Consists of: Diagonal sections and assembly of the bar connectors. Drilling of the holes for the panel holders.				


megawood® LIMES door assemply						
Art. no.	Profile	Art. name	Colour	LxWxH mm		
MWKONF0004		Konfektion LIMES Tür Consists of: Assembly of the filling. Door elements are only supplied including infill. Please order the infill separatly.				

# CARE INSTRUCTIONS

#### What to do about stains and spots?

#### Comprehensive and exten sive testing in our lab has yielded the following results:

We exposed our boards for bare feet to the most common types of soiling and staining. The results have shown that plain water, commonly used cleaning tools, and a little patience are the best solution with normal stains. After cleaning with plain water and several days of light exposure, most of the stains were no longer visible. Always avoid stains due to fine dusts (such as soot and metal dust). These may permanently stain your floorboards.



# CARE INSTRUCTIONS



Naturally-occurring fibre content before treatment



Naturally-occurring fibre content after mechanical treatment with tools (e.g. Brass brush, chisel or by natural weathering)

#### Naturally occurring bast fibre content

megawood® consists of up to 75 % wood fibre. This is specially treated, dried and added to the production process in a contained environment. The raw materials can contain small quantities of other natural fibres such as bast or skin fibre.

These particles can rise to the surface due to water absorption through weathering.

This should not exceed a maximum of 0,03% of the surface area, while the particles' size should not exceed 0,5 cm<sup>2</sup>. These particles will dissolve over time through normal wear when the terrace is in use. They can also be removed mechanically with tools, without damaging the product.

Following the guidance of the EPLF (European Producers of Laminate Flooring), the accepted size of the particles is estimated from head height under direct vertical light.







Scouring powder, 2 Kg bag

#### Water stains

Partially covered terraces can be subjected to water stains in the transitional area between the covered and the uncovered area. Rainwater is flushed over the terrace surface to the cover before it drys off later. This subjects dust particles to temporary moisture before they dry off and remain on the surface. This effect occurs only slightly in the uncovered area which is permanently subjected to sun and rain and it is normally caused by the conditions on site. This does not impair the quality and is therefore not deemed to be a ground for complaint. The water stains can normally be removed using water and conventional cleaning devices.

This effect lessens in time but cannot be entirely avoided.

#### Scouring powder

for powerful cleaning of heavily soiled megawood® terrace surfaces. It is free of tensides and other chemicals and there is no danger to the ground water..

- ❖ 2 kg scouring powder are sufficient for approx. 20 sgm surface.
- ❖ Do not process sensitive surfaces or mask them beforehand.
- \* Do not use on co-extruded decks!

The safety data sheet and the list of ingredients can be found at: https://www.novo-tech.de/service



# CARE TIPS

### timeline

	Initial cleaning	7 days	14 days
Blackberry			
Coffee			
Mustard			
Ketchup			
Cream dressing			
Red wine			
Copper paste			
Soot, Oil			

# COLOUR DEVELOPMENT

### megawood® boards & visual protection elements

The very high dosing accuracy results in a very good homogeneity of the product. Our products are not producted in a discontinuous but a continuous process. The materials to be mixed are pressed into the mould using high pressure and a melt extruder. Rotating steel brushes are then used to remove the polymer surface that results in an optically textured wooden surface. The natural wood material contributes to our innovative product with its natural characteristics and properties. The visible colour variations can be caused by the reactions of the lignin.

Once finished, the product starts out with a bright glossy hue. Please note that this is a natural product and as such is subject to colour maturation due to exposure to light, temperature, and air. The processed wood shaving darkens over the first week from a slightly yellowish glow to a deep, elegant colour hue. It is important that the floorboards for bare feet are installed in the direction of the grain (installation arrow) since the fibre orientation may otherwise result in a varying surface effect (lawnmower effect).



The natural colour maturation is checked with accelerated weathering test and instruments. Sunlight and humidity is simulated with periodic changes; 1000 hours of weathering correspond with approx. one year of outdoor exposure. The quality of our products is checked daily. The product is not forwarded to the shipping department until the quality inspection is complete.





### Association of the German Wood-Based Panel Industry



# Environmental Product Declaration for WPC terrace floorboards and facade elements

An EPD (Environmental Product Declaration) is a multi-page document that describes the environmental impacts of building products based on an ecological assessment using quantitative data. The declaration is prepared by the manufacturer, tested at IBU (Institut Bauen und Umwelt e.V. [German Institute for Construction and Environment]) by independent verifiers based on the ISO 14025 and EN 15804 standards and is then subsequently published.

Environmental product declarations carry the information of the utilised building products that are required for a sustainability / environmental assessment on a building level. They contain information throughout the entire lifecycle, starting at the point of their manufacture, documentation of the base materials used for the product, the opportunities in terms of their processing and disposal as well as the detailed results of the product ecological assessments.

NOVO-TECH GmbH & Co. KG has also documented the environmental compatibility of its products by means of environmental product declarations (EPDs).



Together with the Association of the German Wood-Based Panel Industry, we are committed to sustainable construction by means of EPDs for WPC terrace floorboards and facade elements at IBU.

# **IMPREGNATION**

#### for indoor use

With megawood® indoor protect, we have, for the first time, developed a product that now also permits a true indoor application of boards (such as conservatories) and protects your floorboards against staining. Soiling on megawood® floorboards installed outdoors does not represent a problem as the natural weathering, thanks to the fluctuation between sunlight (UV light) and watering (rain), breaks up the organic compounds and ensures that the patches more or less disappear within a few days or weeks.

This weathering effect is not especially pronounced indoors. Only a slight application of megawood® indoor protect is required in order to achieve the desired effect. Furthermore, the colour of your terrace becomes more intense and a harmonious, natural wood appearance is achieved.

Please note that the impregnation may only take place on clean floorboards and should also be repeated where necessary. We recommend treating the decking prior to the first use.

The maintenance product is thinly and evenly applied to smooth surfaces using a sponge or cloth and is subsequently wiped away using a dry, soft textile cloth so that the excess indoor protect is fully removed.

The maintenance product is thinly and evenly applied to profiled surfaces using a brush and is subsequently wiped away using a dry, soft textile cloth so that the excess indoor protect is fully removed.



### Application for PREMIUM and PREMIUM PLUS boards



#### **Application for CLASSIC boards**



# **CERTIFICATE**

**Indoor Protect** 





akkreditiert durch die Deutsche Akkreditierungsstelle GmbH (DANS)

### PRÜFUNGSZEUGNIS

CT-14-06-23-3

Produkt: PNZ Megawood Indoor Protector

Firma: PNZ Produkte GmbH

Eichstätter Straße 2-4a 85110 Kipfenberg

Auftrag: Bestimmung ausgewählter Oberflächeneigenschaften

Prüfmethodik: Bestimmung des Migrationsverhaltens von Schwermetallen

nach DIN EN 71-3 (2013:07)

Prüfbericht: 2514261 vom 02. Juni 2014

Prüfergebnis: Migrationsverhalten

Das getestete Produkt hält die Anforderungen an die Konzentrationen eluierbarer Schwermetalle Aluminium (Al), Antimon (Sb), Arsen (As), Barium (Ba), Bor (B), Cadmium (Cd), Kobalt (Co), Chrom (Cr), Kupfer (Cu), Quecksilber (Hg), Mangan (Mn), Nickel (Ni), Blei (Pb), Selen (Se), Zinn (Sn), Strontium (Sr) und Zink (Zn) entsprechend DIN EN 71-3

(2013:07) Klasse III vollständig ein.

Dresden, 23.Juni2014

i.l. h. rsn

Leiter des Prüflaboratoriums



a. Sucho-la verantwortlicher Bearbeiter

# **QUALITY STANDARDS**

### megawood® boards

#### Mechanical characteristics boards CLASSIC, CLASSIC Varia, SIGNUM, PREMIUM, PREMIUM Plus, DYNUM und DELTA

#### Three-point bending sc 40x60 mm:

Bearing distancer: 440 mm

Centre distance: 500 mm

Test speed: 20 mm/min

Breaking load: mind. 3.400 N\*

#### Three-point bending sc 80x60 mm:


Bearing distancer: 440 mm

Centre distance: 500 mm

Test speed: 20 mm/min

Breaking load: mind. 3.400 N\*





### 3. Mechanical characteristics construction plank 40 x 112 mm

#### Three-point bending:


Bearing distancer: 960 mm

Centre distance: 1,000 mm

Test speed: 20 mm/min

Breaking load: min. 3,400 N\*

\* 3,400 N equals  $\approx$  340 kg/board at a maximum distance of 100 cm between the supporting beams.




#### Mechanical characteristics construction plank 40x145 mm

#### Three-point bending:

Bearing distancer: 1,160 mm
Centre distance: 1,200 mm
Test speed: 20 mm/min
Breaking load: min. 3,400 N\*

\* 3,400 N equals ≈ 340 kg/board at a maximum distance of 120 cm between the supporting beams.



#### 5. Permissible dimension change after water absorption

Permissible dimension change after water absorption* megawood® boards							
Dimension	Measuring point	Permissible dimension change Guaranteed values		Notes			
Length	Maximum value	Board length 300 cm Board length 360 cm Board length 420 cm Board length 480 cm Board length 540 cm Board length 600 cm	≤ 9.0 mm ≤ 10.8 mm ≤ 12.6 mm ≤ 14.4 mm ≤ 16.2 mm ≤ 18.0 mm ≤ (3 mm/m)	Pay attention to distances of fixed component parts			
Width (max. 295 mm)	Middle of board		max. ≤ 0.9 mm				
Thickness (max. 25 mm)	Middle of board		max. ≤ 0.5 mm				


 $<sup>\</sup>ensuremath{^*}$  with outdoor exposure and installation acc. to assembly instructions

# TECHNICAL INFORMATION

megawood® boards


### megawood® board and Bangkirai

Abrasion resistance comparison test





#### Abrasion resistance test conditions



#### Material description

megawood® is a polymer-bonded wood material and contains of up to 75 % wood fibres, high-value polymers, suitable additives and colorants.

#### Distinctive characteristics and advantages

- High resistance against external environmental impacts
- Easy to work with same as normal wood
- Installed with clamp system
- Environment-friendly and recyclable

- Up to 75 % renewable raw materials
- Dyed throughout and surface-ready
- Resistant to mould fungus IHD-Standart 20-25 (2006)

Technical data				
Characteristics		Measuring unit	megawood®1	Quality seal class <sub>2</sub>
Density		g/cm³	> 1.3	
Breaking strength*)		N	≥ 4,000	≥ 3,300
Bending at 500 N		mm	≤ 1.8	≤ 1.9
Swelling after cold water storage	Volume	Weight %	≤ 2.0	≤ 7.0
(28 days)	Lengthwise	%	≤ 0.3	≤ 0.4
	Width	%	≤ 0.3	≤ 0.8
	Thickness	%	≤ 1.7	≤ 4.0
Skid resistance	Slip class		min. R 10	min. R 10
Thermal flexural behaviour		mm	∆s ≤ 10	∆s ≤ 10
Behaviour during the freeze-thaw test	Breaking load	Δ %	≤ 20	≤ 20
Thermal expansion coefficient		10 <sup>-6</sup> / K	20	≤ 40

These values have been determined with test specimens and may vary depending on production. They are therefore only approximate values.

- \*) This value applies to single floorboard upon centre distance between support points (mid of support) of 50 cm!
- 1) Static mean values for megawood® boards. Individual data sheets per plank can be requested separately.
- 2) Static mean values for achieving the quality seal, conform to the EU Safety Standard EN 15534-1 and the EU product standard EN 15534-4.

Production-related measure tolerances <b>megawood</b> ® boards				
Specifications Tolerance zone				
Profile length	300, 360, 420, 480, 540, 600 cm	-0.0/+ 10.0 mm		
Profile width	145 mm, 195 mm, 242 mm, 293 mm	-2.0/+ 1.0 mm		
Profile thickness	21 mm, 25 mm	-1.0/+ 1.0 mm		


# **QUALITY STANDARDS**

### General Building Approval (abZ)

In accordance with the General Building Approval (abZ), the **DYNUM 25 x 293 mm (Cardamom & Nigella)** and **PREMIUM Jumbo 21 x 242 mm (nut brown & basalt grey)** terrace boards can be used as a load-bearing floor for roof terraces, pergolas, loggias, balconies, escape landings, catwalks and similar in addition to stairs and stair landings in residential buildings and office buildings conform with the DIN EN 1991-1-1/NA1 standard, Table 6.1 DE, Categories T1, T2 und Z. The bearing floor is to be at least a multi-field support (at least a two-field support) and it is to be installed so that the terrace boards are visible and can always be replaced.

The terrace boards are only to be laid and mounted by companies that have the necessary experience. The bearing substructure is to be of wood or steel. The terrace boards are to be mounted on each of the supports on both of the longitudinal sides by them being placed on the wood or steel substructure and then fixed in place using a stainless steel clip and screw. Only terrace boards with a full width are to be laid and a cutting to size along the longitudinal edge is not permitted. No damaged terrace boards are to be mounted. The terrace boards can be laid in the direction of the span (in a longitudinal direction of the board) with a gradient of max. 2%. The drilling of holes or the creating of breakthroughs in the terrace boards is basically not permitted.


#### 1. Laying the PREMIUM Jumbo terrace boards on a wood or steel structure




#### Three-point bending:

Centre distance: 400 mm Breaking load: min. 9,100 N\*

\* 9,100 N equals  $\approx$  910 kg/board at a maximum distance of 40 cm between the supporting beams.




#### 2. Laying the DYNUM terrace boards on a wood or steel structure



#### Three-point bending:

Centre distance: 650 mm
Breaking load: min. 8,500 N\*

\* 8,500 N equals ≈ 850 kg/board at a maximum distance of 65 cm between the supporting beams.



# **CERTIFICATE**

General Building Approval (abZ)

Allgemeine bauaufsichtliche Zulassung/ Allgemeine

Bauartgenehmigung

Deutsches Institut für Bautechnik

#### Zulassungsstelle für Bauprodukte und Bauarten

#### Rautechnisches Prüfamt

Eine vom Bund und den Ländern gemeinsam getragene Anstalt des öffentlichen Rechts Mitglied der EOTA, der UEAtc und der WFTAO

Datum: Geschäftszeichen: 21.09.2020 171-1.10.9-506/2

#### Nummer:

Z-10.9-506

#### Antragsteller:

NOVO-TECH GmbH & Co. KG Siemensstraße 31 06449 Aschersleben

#### Geltungsdauer

vom: 21. September 2020 bis: 21. September 2025

#### Gegenstand dieses Bescheides:

Barfußdielen "megawood" Typ "PREMIUM Jumbo massiv 21x242 mm" und "DYNUM massiv 25x293 mm" aus Holz-Polymer-Verbundwerkstoff für tragende Böden

Der oben genannte Regelungsgegenstand wird hiermit allgemein bauaufsichtlich zugelassen und genehmigt.

Dieser Bescheid umfasst neun Seiten und vier Anlagen mit 10 Seiten.



DIBt | Kolonnenstraße 30 B | D-10829 Berlin | Tel.: +493078730-0 | Fax: +493078730-320 | E-Mail: dibt@dibt.de | www.dibt.de

### Fraunhofer Institut for Mechanics of Materials



#### Fraunhofer

Institut Werkstoffmechanik

Fraunhofer IWM Heideallee 19 06120 Halle

Novo-Tech GmbH & CoKG Mr. Sasse Institutsleiter Prof. Dr. Peter Gumbsch

Heideallee 19 066120 Halle

Wöhlerstraße 11 79108 Freiburg

Telefon +49 (0) 345/55 89-0 Telefax +49 (0) 345/55 89-1 01 www.iwmh.fraunhofer.de

Steffen Meinicke Telefon +49 (0) 3 45/55 89-436 Telefax +49 (0) 3 45/55 89-1 01 Steffen.Meinicke@iwmh.fraunhofer.de

Halle, 15.03.2006

#### Test report

Dear Mr. Sasse,

below you can find your floorboard characteristic values (samples taken from production dated 26.01.2006 and 28.01.2006) determined in-house by our company.

#### 1. Determination of thermal expansion coefficient

The determination of the thermal coefficient has been carried out acc. to DIN EN 13471. The determination of the characteristic values hasthree directions using a non-contact measuring system. The measurement has been executed within a temperature range of 25°C to 80°C.


The expansion has been measured at the profile surface in length (extrusion direction) and width (laterally to extrusion direction), as well as the profile cross-section width and thickness [depth] of profile).

Vorstand der Fraunhofer-Gesellschaft Univ.-Prof. Dr. Ing. habil. Prof. e.h. Dr. h.c. Hans-Jörg Bullinger, Präsident Dr. rer. pol. Alfred Gossner Dr. jur. Dirk-Meints Polter Prof. Dr. Dennis Tsichritzis

Fraunhofer-Gesellschaft zur Förderung der angewandten Forschung e.V. München

Bankverbindung: Deutsche Bank, München Konto 7521933 BLZ 700 700 10 IBAN: DE86 7007 0010 0752 1933 00. BIC (Swift-Code): DEUTDFMM

### Fraunhofer Institut for Mechanics of Materials



#### 2. Determination of water absorption and thickness swelling

Determination of thickness swelling after water absorption following DIN EN 317 has been carried out with test specimens prepared from the component part (profile with 145 mm length). The samples have been stored in resting water (pH-value 7 +/- 1) at  $(20 +/- 2)^{\circ}$  C. The swelling measurement is taken at the following times: 1d, 7d, 14d, 28d, 42d. The water absorption is determined gravimetrically (times same as with swelling).


[d]	Floorboard	26.01. [mm]	water absorption
	1	b	[%]
0	145.02	145.58	0.0
1	145.05	145.70	0.9
7	145.16	145.89	2.9
14	145.45	146.15	4.3
21	145.39	146.19	5.2
28	145.49	146.42	5.9
40	145.68	146.72	7.1


[d] Floorboard 28.01		er absorption
1	b	[%]
0 145.15	145.41	0.0
1 145.10	145.45	1.0
7 145.25	145.65	2.9
	145.78	4.4
21 145.41	145.91	5.3
28 145.47	146.09	5.8
40 145.51	146.30	7.0

### Fraunhofer Institut for Mechanics of Materials


#### 3. Determination of bending creep behaviour at increased temperature

The creep behaviour has been determined according to DIN ISO 899-2 using a bending creep test with a three-point bending procedure. The measurement has been executed in a climatic chamber. The test has been carried out wit-hin a period of 150 hours and at 50 $^{\circ}$  C as well as 50% r.H. The support dis-tance was 440 mm. The samples have been impinged with a constant load of 100 kg. The following table lists the test results.





#### Floorboard NOVO-TECH NP 2601 (creep test)



Page 3

### Fraunhofer Institut for Mechanics of Materials

#### 4. Determination of E modulus in 3-point bending test

To determine the E-modulus, breaking strength and maximum deflection, a 3-point test with a support distance of  $440~\mathrm{mm}$  has been conducted with profiled parts  $550-\mathrm{mm}$  in length.

Sample	E-modulus	max. strength	max. deflection
	[N/mm²]	[N]	[ mm ]
26.01.2006	3576	3643	14
28.01.2006	3392	3514	14
14.02.2006	3489	3544	26
15.02.2006	3467	3570	26

If there are any questions concerning this test report, please do not he sitate to contact  $\ensuremath{\mathsf{me}}\xspace.$ 

Sincerely yours

Steffen Meinicke

225 009

#### 1. Test of resistance to mould fungi

#### 1.1 Test information

#### Test principle:

Shaped test specimens have been exposed to mould fungi attack by inoculating defined mixture of spores. Because test material is intended for outdoor use, one portion of test specimens was put to strain by washing-out prior to biological test. In order to simulate nutrient dragging by pollution in practise, testing additionally has been executed under intensified conditions, i.e. by adding a nutrient solution. The test formulations have been incubated for four weeks under conditions that support growing and germinating of mould fungi. The evaluation of mould fungi vegetation as test criterion has been carried out after 7, 14 and 28 days according to defined bonitation key.

#### Test variants:

- Standard test without nutrient solution without aging
- Standard test without nutrient solution and strain of washing-out
- Intensified test with nutrient solution without aging
- Intensified test with nutrient solution and strain of washing-out

#### Underlying test procedure:

The test has been carried out in accordance with IHD Standard [Institute for Wood Technology Dresden] 20-25 (2006): "Test of resistance to mould fungi of construction and wood materials" based on EN 60068-2-10:2005 "Environmental influences - Parts 2-10: Test procedures - Test J and guideline: mould growth" (IEC 60068-2-10:2005).

#### Tested fungi:

Aspergillus niger, Paecilomyces variotii, Penicillium funiculosum, Trichoderma viride, Chaetomium globosum

#### **Cultivation conditions:**

28 days' incubation in incubator at 29°C and 95 % relative air humidity

#### Sterilisation procedure:

Pressure cooker (100°C, 2x)

#### Aging strain prior to test:

Saturation without vacuum during 7 days with 6 times water exchange (following DIN EN 84)

#### Test specimen dimensions:

Test material: 50x20x5 mm<sup>3</sup>

Reference material: 50x25x15 mm³ (pine splint), 60x60x20 mm³ (MDF)

#### Date of test specimen installation / removal:

26.01.2006 / 23.02.2006

225 009

#### 1.2 Results

Table 3: Test without prior strain of washing-out:

Vegetation on test specimen top surface after 28 days (Average values each time from 6 individual values)

No.	Material	Average rating number			
		External infection		Self in	fection
п		Standard- test	Intensified test	Standard- test	Intensified test
1)	WPC H40-05, grey	1	1	1	1
2)	WPC H41-05, brown	1	1	1	1
3)	Bangkirai	1	3	1	3

#### Table 4: Test after prior strain of washing-out:

Vegetation on test specimen top surface after 28 days (Average values each time from 6 individual values)

No.	Material	Average rating number			
		External infection		Self in	fection
		Standard- test	Intensified test	Standard- test	Intensified test
1)	WPC H40-05, grey	1	1	1	1
2)	WPC H41-05, brown	1	1	1	1
3)	Bangkirai	1	3	1	3

#### Evaluation scheme:

- O No mould fungi detectable on the test specimen surface upon examination under reflected-light microscope at 50-fold enlargement.
- 1 Mould fungi not or barely detectable with unaided eye; however, clearly at 50-fold enlargement detectable.
- 2 Mould fungi vegetation clearly detectable with unaided eye and clearly lower than on comparison test specimen.
- 3 Mould fungi vegetation clearly detectable with unaided eye and equal to or stronger than on comparison test specimen.

Table 5: Wood humidity after test **without prior strain of washing-out** (average values each time from 6 individual values)

No.	Material	Average rating number			
		External	infection	Self in	fection
		Standard- test	Intensified test with nutri- ent solution	Standard- test	Intensified test with nutri- ent solution
1)	WPC H40-05, grey	13.7	13.3	12.0	13.1
2)	WPC H41-05, brown	12.0	11.7	11.4	12.1
3)	Bangkirai	21.6	21.3	19.3	20.2
4)	Ref. pine splint	26.9	27.4	26.8	27.0
5)	Ref. light MDF	26.4	26.2	29.2	25.1

225 009

Table 6: Wood humidity after test with prior strain of washing-out (average values each time from 6 individual values)

No.	Material	Average rating number				
		External	infection	Self in	fection	
		Standard- test	Intensified test with nutri- ent solution	Standard- test	Intensified test with nutri- ent solution	
1)	WPC H40-05, grey	13.7	14.9	13.5	12.6	
2)	WPC H41-05, brown	13.1	12.7	12.1	12.3	
3)	Bangkirai	21.7	20.9	20.4	21.6	
4)	Ref. pine splint	27.2	27.6	27.1	27.4	
5)	Ref. light MDF	25.3	26.3	26.9	27.6	

#### 1.5 Evaluation / summary

As a result of structure and colour of WPC material, mould fungi vegetation was not detectable with unaided eyes (Fig. 3). Inspection under reflected-light microscope, however, has provided evidence, that mould fungi were grown on tested variants "H40-05" and "H41-05" (Fig. 5 to 11), but at a clearly lower level than on both comparison test specimens from MDF and pine splint. The vegetation on Bangkirai was low with standard tests and strong with intensified test conditions when additional nutrients were supplied. The strain of washing-out on WPC and Bangkirai had no significant influence on resistance to mould fungi.

#### Evaluation of resistance to mould fungi is based on following scheme:

(IHD works standard VA20-25):

Bonitation level	Field of application		
	Internal area <sup>1)</sup>	External area <sup>2)</sup>	
0	resistant	resistant	
1	reduced resistant	resistant	
2	not resistant	reduced resistant	
3	not resistant	not resistant	

<sup>1)</sup> All areas, where material is in contact with room air of restrooms

Because the tested materials are terrace covering for external area, result of test variant "Intensified Test with strain of washing-out" will be used for final evaluation: According to that, WPC variants "H40-05" and "H41-05" have proved resistant to mould fungi for outdoor use, however, Bangkirai by contrast was not resistant.

Whe Phis


Dresden, 28.02.2006

**Katharina Plaschkies,** Master's in Biology Responsible person in charge

<sup>&</sup>lt;sup>2)</sup> All areas, which do not comply with internal area's definition

225 009

#### 1.4 Photos



**Fig. 3:** Selected test specimen after mould fungi test: no vegetation macroscopically detectable




Fig. 4: Reference test specimen after mould fungi test: vegetation clearly detectable (above: MDF, below: pine splint)



Fig. 5: Mould fungi on test specimen 10 (H40), 40-fold enlargement





Fig. 6: Mould fungi on test specimen 22 (H41), 40-fold enlargement



**Fig. 7:** Mould fungi on test specimen 59 (H40), 40-fold enlargement



Fig. 8: Mould fungi on test specimen 72 (H41), 70-fold enlargement



**Fig. 9:** Mould fungi on test specimen 77 (Bangkirai), 50-fold enlargement



**Fig. 10:** Mould fungi on test specimen 122 (H41), 40-fold enlargement



**Fig. 11:** Mould fungi on test specimen 161 (H40), 40-fold enlargement

# TECHNICAL SAFETY INFORMATION

1.) Material/Manufacturer Designation

Product designation: megawood®

Material/substance type: Polymer bonded wood material

Use: Production of extruded profiles and injection moulding elements

Manufacturer: NOVO-TECH GmbH & Co. KG

Siemensstraße 31 • 06449 Aschersleben • Germany

Tel.: +49 (0) 3473 / 22503 - 0 Fax: +49 (0) 3473 / 22503 - 15

2.) Chemical Composition/Information about Components

Composition: Cellulose CAS-Nr.: 9004-34-6 30 – 40%

Hemicellulose CAS-Nr.: 9025-53-2 18 - 24 % Lignin CAS-Nr.: 9005-53-2 12 - 16 % HDPE CAS-Nr.: 9002-88-4 10 - 40 %

3.) Possible Hazards

No risks to health and environment if used and handled appropriately.

4.) First Aid Measures

No special measures required.

5.) Fire Prevention Measures

Suitable extinguishing agents: Water spray, foam, CO<sub>2</sub>, powder

6.) Measures in Case of Unintentional Release:

For people: No special measures required

Cleaning: Absorb mechanically (e.g. vacuuming)

7.) Handling and Storage

Storage: Smoking prohibited in storage area.

Fire protection measures:

No open flame.

Handling: To avoid electrostatic discharges, the production and

transport equipment should be made from electrically

conductive material and be well earthed.

With thermal processing: Extract vapours and/or ensure working areas are

sufficiently ventilated.

8.) Exposure Limit and Personal Protective Equipment

Work hygiene: Comply with general protective and hygiene measures:

Always wash hands before eating, drinking, smoking or

using the W.C..

General safety measures: Ensure that working areas are sufficiently ventilated and have

adequate extraction systems.

Skin protection / Eye protection: Not required

9.) Physical and Chemical Properties

Form: Wood-polymer optics

Colours: Brown, black, multicoloured

Odour: Woody pH value (with 100g/l  $H_2O$  and  $20^{\circ}C$ ): 4.5-6.5

Melting point: Not applicable

Fire protection classification: Flame retardant material according to DIN EN 13501-1:2010,

Classification normal: D<sub>fl</sub>-s1 (old B2)

Classification difficult: C<sub>fl</sub>-s1

Boiling point (1013 hPa): Not applicable

Flashpoint: Not applicable

Ignition point: Approx. 420°C (DIN 51 795)

Explosion limits: Not applicable

# **TECHNICAL SAFETY** INFORMATION

Toy fitness after DIN EN 71-3 Migration:

Vapour pressure (20°C): Not applicable Density (20°C):  $>1.3 \text{ g/cm}^3$ Solubility in water (20°C): Insoluble

Product designation: Polymer bonded wood material

10.) Stability and Reactivity

Stability: Product is stable under normal conditions.

Thermal decomposition starts at approx. 180°C.

Dangerous reactions: None known

Incomplete combustion releases carbon monoxide and Hazardous decomposition products:

possibly other hazardous substances such as soot, for example.

11.) Allergens

The product does not contain any of the 14 allergen materials that are subject to mandatory declaration in accordance with the EU Food Information Regulation 1169/2011.

12.) Toxicological Information

No damaging effects when handled appropriately

13.) Ecological Information

The product is a wood polymer mixture insoluble in water with no negative environmental impact on ecosystems. Up to 75 % of the product is made from renewable resources.

14.) Disposal Notes

According to the European Waste Catalogue (EWC), wood PE belongs to the group of wastes from wood processing and the manufacturing of boards and furniture and to the waste type of sawdust, chips, cut waste, wood, chipboard and veneers without toxic substances, Code 03 01 05. The product can be recycled 100 % using suitable process technology. The product must be disposed of in accordance with disposal and treatment rules and regulations of the local authorities (e.g. waste incineration, waste dumps).

15.) Transport Information

Not subject to mandatory labelling/marking acc. to Directive 67/548/EEC, the Hazardous Substances Ordinance (GefStoffV) and other rules and regulations. Not a hazard acc. to applicable transport rules and regulations.

16.) Wind load strain of terrace surfaces

Lifting loads caused by wind suction must be taken into consideration when dealing with terrace floorboards that are laid parallel to the supporting construction. Dead weight in combination with the respectively designed sub-construction must compensate for these lifting loads. Depending on the plank thickness and the associated sub-construction, no lifting of the planks is expected in normal areas. Prevention against lifting must be planned on the basis of the guidelines and standards in exposed terrace areas, in the event of special boundary conditions as well as in particularly high locations.

17.) Rules and Regulations

EEC marking: Not subject to mandatory marking acc. to EEC rules and regulations.

Hazard symbols, R-phrases and S-phrases: Not required.

Water pollution class: WPC 0 (not hazardous).

18.) Additional Information

The information supplied here corresponding with current findings, knowledge, and experiences, are to describe the product's safety aspects. However, this information is not associated with any warranty or quarantee of product properties. This product safety sheet was prepared according to the second revision of Directive 91/155/EEC based on Directive 2001/58/EU of the commission dated July 27, 2001.

This safety data sheet applies to the following: megawood® Polymer bonded wood materialf 20.08.2018

Rev. Level:

# FORMS OF DELIVERY AND PACKAGING UNITS

megawood® DELTA	(21 x 145 mm)	p	ackage content 70 pcs.	
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
420	294.00	17.01*	42.63	1,190.70*
480	336.00	19.44*	48.72	1,360.80*
600	420.00	24.30*	60.90	1,701.00*

megawood® CLASSIC	р	ackage content 98 pcs.		
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
300	294.00	9.51*	42.63	931.98*
360	352.80	11.41*	51.16	1,118.38*
420	411.60	13.31*	59.68	1,304.77*
480	470.40	15.22*	68.21	1,491.17*
540	529.20	17.12*	76.73	1,677.56*
600	588.00	19.02*	85.26	1,863.96*

megawood® CLASSIC Jumbo (21 x 242 mm) package content 56 pcs				
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
420	235.20	24.36*	56.92	1,364.16*
480	268.80	27.84*	65.05	1,559.04*
600	336.00	34.80*	81.31	1,948.80*

megawood® CLASSIC Varia (21 x 195 mm)				ackage content 60 pcs.
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
420	252.00	21.13*	49.14	1,267.56*
480	288.00	24.14*	56.16	1,448.64*
600	360.00	30.18*	70.20	1,810.80*

megawood® PREMIUN	И (21 x 145 mm)	р	ackage content 84 pcs.	
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
420	352.80	14.66*	51.16	1,231.27*
480	403.20	16.75*	58.46	1,407.17*
600	504.00	20.94*	73.08	1,758.96*

megawood® PREMIUM	р	ackage content 48 pcs.		
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
420	201.60	25.79*	48.79	1,237.82*
480	230.40	29.47*	55.76	1,414.66*
600	259.20	33.16*	62.73	1,591.49*

<sup>\*</sup> These weights are approximate. Production processes may vary these weights up to 5% of the guideline.

# FORMS OF DELIVERY AND PACKAGING UNITS

megawood® PREMIUN	р	ackage content 84 pcs.		
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
420	352.80	14.66*	51.16	1,231.27*
480	403.20	16.75*	58.46	1,407.17*
600	504.00	20.94*	73.08	1,758.96*

megawood® PREMIUN	ackage content 48 pcs.			
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
420	201.60	26.21*	48.79	1,257.98*
480	230.40	29.95*	55.76	1,437.70*
600	288.00	37.44*	69.70	1,797.12*

megawood® SIGNUM (21x145 mm) package content 84 p				
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
360	302.40	12.89*	43.85	1,082.59*
420	352.80	15.04*	51.16	1,263.02*
480	403.20	17.18*	58.46	1,443.46*
540	453.60	19.33*	65.77	1,623.89*
600	504.00	21.48*	73.08	1,804.32*

megawood® SIGNUM Jumbo (21x242 mm) package content 48 pcs				
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
360	172.80	22.32*	41.82	1,071.36*
420	201.60	26.04*	48.79	1,249.92*
480	230.40	29.76*	55.76	1,428.48*
540	259.20	33.48*	62.73	1,607.04*
600	288.00	37.20*	69.70	1,785.60*

megawood® DYNUM (21x242 mm) package content 48 pcs				ackage content 48 pcs.
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
420	201.60	26.75*	48.79	1,284.19*
480	230.40	30.58*	55.76	1,467.65*
600	288.00	38.22*	69.70	1,834.56*

megawood® DYNUM (25 x 293 mm)			package content 30 pcs.	
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
420	126.00	38.60*	36.92	1,157.94*
480	144.00	44.11*	42.19	1,323.36*
600	180.00	55.14*	52.74	1,654.20*

<sup>\*</sup> These weights are approximate. Production processes may vary these weights up to 5% of the guideline.

# FORMS OF DELIVERY AND PACKAGING UNITS

### megawood® decking

megawood® sub construction (40 x 60 mm)			ра	ckage content 170 pcs.
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
360	612.00	9.29*	36.72	1,578.96*

megawood® sub construction (80 x 60 mm)			р	ackage content 68 pcs.
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
400	272.00	12.32*	16.32	837.76*

megawood® connector (28 x 76 mm) package content 52 p				ackage content 52 pcs.
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
360	187.20	3.78*	14.23	196.56*

	package content	Package dimensions	Unit	Forms of delivery	
Board DELTA 21 x 145 mm	70 pcs. per 7 pcs. side by side, per 5 pcs. stacked	1,020 x 310 mm Length 420 to 600 cm	per 2 pcs. completely foil-covered	Per bundle on untreated square support boards; bundle straps and edge protectors	
Board CLASSIC 21x145 mm	98 pcs. per 7 pcs. side by side, per 14 pcs. stacked	1,020×400 mm Length 300 to 600 cm	per 2 pcs. completely foil-covered	Per bundle on untreated square support boards; bundle straps and edge protectors	
Board CLASSIC Jumbo 21 x 242 mm	56 pcs. per 4 pcs. side by side, per 14 pcs. stacked	1,020x400 mm Length 420 to 600 cm	per 1 pc. completely foil-covered	Per bundle on untreated square support boards; bundle straps and edge protectors	
Board CLASSIC Varia 21x195 mm	60 pcs. per 5 pcs. side by side, per 12 pcs. stacked	980x360mm Length 420 to 600cm	per 2 pcs. completely foil-covered	Per bundle on untreated square support boards; bundle straps and edge protectors	
Board PREMIUM PREMIUM PLUS 21x145 mm	84 pcs. per 7 pcs. side by side, per 12 pcs. stacked	1,020 x 400 mm Length 300 to 600 cm	per 2 pcs. completely foil-covered	Per bundle on untreated square support boards; bundle straps and edge protectors	
Board Jumbo PREMIUM PREMIUM PLUS 21 x 242 mm	48 pcs. per 4 pcs. side by side, per 12 pcs. stacked	1,020x400 mm Length 300 to 600 cm	per 1 pc. completely foil-covered	Per bundle on untreated square support boards; bundle straps and edge protectors	

<sup>\*</sup> These weights are approximate. Production processes may vary these weights up to 5% of the guideline.

## megawood® decking

	ma alcama assutant	Do also no dino anciene	I In it	Farmer of delivery
	package content	Package dimensions		Forms of delivery
Board SIGNUM 21 x 145 mm	84 pcs. per 7 pcs. side by side, per 12 pcs. stacked	1,020x400mm Length 300 to 600cm	per 2 pcs. completely foil-covered	Per bundle on untreated square support boards; bundle straps and edge protectors
Board SIGNUM Jumbo 21 x 242 mm	48 pcs. per 4 pcs. side by side, per 12 pcs. stacked	1,020x400mm Length 300 to 600cm	per 1 pc. completely foil-covered	Per bundle on untreated square support boards; bundle straps and edge protectors
Board DYNUM 21 x 242mm	48 pcs. per 4 pcs. side by side, per 12 pcs. stacked	1,020 x 400 mm Length 360 to 600 cm	per 1 pc. completely foil-covered	Per bundle on untreated square support boards; bundle straps and edge protectors
Board DYNUM 25 x 293mm	30 pcs. per 3 pcs. side by side, per 10 pcs. stacked	880x350mm Length 360 to 600cm	per 1 pc. completely foil-covered	Per bundle on untreated square support boards; bundle straps and edge protectors
Sub construction 40 x 60 mm	170 pcs. per 17 pcs. side by side, per 10 pcs. stacked	1,020 x 500 mm Length 360 cm	per 2 pcs. partially foil-covered	Per bundle on untreated square support boards; bundle straps and edge protectors
Sub construction 80 x 60 mm	68 pcs. per 17 pcs. side by side, per 4 pcs. stacked	1,020 x 420 mm Length 400 cm	not foil-covered	Per bundle on untreated square support boards; bundle straps and edge protectors
Connector 28 x 76 mm	52 pcs. per 13 pcs. side by side, per 4 pcs. stacked	988x112mm Length 360cm	per 2 pcs. partially foil-covered	Per bundle on untreated square support boards; bundle straps and edge protectors

## megawood® decking

megawood® fastening	package content in packing units
Locking clamp, one-piece, blackened, 50 pcs. incl. 17 screws	48 pack
Locking clamp, one-piece, blackened, 250 pcs. incl. 85 screws	20 pack
Locking clamp edge, one-piece, blackened, 25 pcs./pack	24 pack
Clip, blackened, 50 pcs./pack	25 pack
Clip, blackened, 250 pcs./pack	24 pack
Clip, blackened, 500 pcs./pack	20 pack
Edge clip, blackened, 25 pcs./pack	25 pack

megawood® accessories sub construction	package content in packing units
Sub construction fixing screws 7.5 x 92 mm incl. bit und drill	20 pack
Sub construction fixing screws 7.5 x 132 mm incl. bit und drill	10 pack
Self-adhesive retaining band 10 mm, 10 m/roll	25 roll
Groove bridge, 20 pcs./pack	20 pack

megawood® accessories	package content in packing units
Rubber pad 60x20x100mm	100 pcs.
Rubber pad 60x10x100mm	100 pcs.
Rubber pad 60 x 3 x 100 mm	100 pcs.
Distance keeper, mounting aid for decking, 10 pcs.	10 pack
Zammer, mounting aid for one-piece locking clamp	10 pcs.
Rolli, additional part for Zammer	10 pcs.
Screw M8 x 80 mm + washer + nut, 10 pcs./pack	25 pack
Screw M8 x 40 mm, 10 pcs./pack	25 pack
Screw M6 x 40 mm, 10 pcs./pack	10 pack
Screw set, 4 x 35 mm, 25 pcs./pack	1 pack
Distanz Fix, 10 pcs./pack	12 pack
Arretier Fix, 20 pcs./pack	12 pack

megawood® accessories profiles and strips	package content in packing units
Groove strip 21 mm, 25 m/roll	10 roll
Groove strip 21 mm, 100 m/roll	10 roll
Groove strip P5, 25 m/roll	10 roll
Groove strip P5, 100 m/roll	10 roll
Ventilation grilles, stainless steel brushed	54 pcs.
House connection profile 55.5 x 45.0 x 1,5 mm / 25 mm	
silver/anthracite anodised; Length 400 cm	10 pcs.
House connection profile 55.5 x 45.0 x 1,5 mm / 21 mm	
bronze/silver/anthracite anodised; Length 400 cm	10 pcs.
Gehrungsprofil, aluminium 50 x 25 mm	
bronze/silver/anthracite anodised; Length 400 cm	10 pcs.
Sealing tape for miter profile 20 mm, 13 m/roll	15 roll

### megawood® FIX STEP system

megawood® FIX STEP plate				
Art. no.	Name	kg/pcs.	pcs./pack	kg/pack
NOVO017-01	Standard plate	2.46*	224	551.04*
NOVO017-02	Edge plate DUO	3.30*	168	554.40*

megawood® FIX STEP fixture	package content in packing units
Standard fixture	224 pcs.
Edge fixture DUO	168 pcs.

## megawood® VARIO FIX system

megawood® VARIO FIX I & II				
Art. no.	Name	kg/pcs.	pcs./pack	kg/pack
MWVFUK100000SW	VARIO FIX I	3.08*	200	546.60*
MWVFUK200000SW	VARIO FIX II	3.24*	200	648.00*

#### megawood® accessories FIX STEP and VARIO FIX

megawood® accessories FIX STEP and VARIO FIX	package content in packing units
Attachment piece elevated installation	80 pcs.
Comfort pad	80 pcs.
Rubber pad 300 x 300 x 3 mm	80 pcs.
Rubber pad 300 x 300 x 5 mm	80 pcs.
Rubber pad 300 x 300 x 10 mm	40 pcs.
Assembly clip, 10 pcs./pack	10 pack
Perforated tape, 10 m/roll	25 roll
Fastening screw for perforated tape 10 pcs.	1 pack

### megawood® cleaning & care

megawood® cleaning & care	package content in packing units
Scouring powder, 2 Kg Tüte	8 pcs.
Scrubbing brush	1 pc.
Scrubbing brush incl. bracket and 2 wing screws	1 pc.
indoor protect 0.75 L	12 pcs.
indoor protect 2.5 L	8 pcs.

## megalite LED lighting system

megawood® LED lighting system	package content in packing units
LED-Linear light for horizontal installation, 27 W	6 pcs.
LED-Linear light for horizontal installation, 36 W	6 pcs.
LED-Linear light for horizontal installation, 45 W	6 pcs.
LED-Linear light for vertical installation, 27W	6 pcs.
LED-Linear light for vertical installation, 36 W	6 pcs.
LED-Linear light for vertical installation, 45 W	6 pcs.
LED-Spot Mini	40 pcs.
LED-Spot Maxi	40 pcs.
2 box distributor	10 pcs.
4 box distributor	10 pcs.
Extension cables 1 m	20 pcs.
Extension cables 3 m	20 pcs.
Extension cables 6 m	10 pcs.
Power supply electronic ballast 40 W	5 pcs.
Power supply electronic ballast 150 W	5 pcs.
Repeater	5 pcs.
Remote control set	5 pcs.
LED bulb, 27 W	1 pc.
LED bulb, 36 W	1 pc.
LED bulb, 45 W	1 pc.
Cover profile for Linear light horizontal installation	1 pc.
Cover profile for Linear light vertical installation	1 pc.
Aluminium profile for Linear light	1 pc.
Aluminium end caps 2 pieces, + 4 stainless steel screws	1 pack

megawood® circular posts (Ø 90 mm) package content 44 pcs				ackage content 44 pcs.
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
220	96.80	18.26*	8.71	803.44*
270	118.80	22.41*	10.69	986.04*

megawood® octagonal posts (90 x 90 mm)			р	ackage content 44 pcs.
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
220	96.80	18.26*	8.71	803.44*
270	118.80	22.41*	10.69	986.04*

megawood® square posts (90 x 90 mm)			р	ackage content 44 pcs.
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
220	96.80	21.12*	8.71	929.28*
270	118.80	25.92*	10.69	1,140.48*

megawood® oval posts (60 x 90 mm)			р	ackage content 44 pcs.
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
220	96.80	12.98*	8.91	571.12*
270	118.80	15.93*	10.93	700.92*

megawood® panel Augusta (270 x 35 x 6mm)			р	ackage content 84 pcs.
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
160.2	134.57	5.13*	36.33	430.62*
180.5	151.62	5.78*	40.94	485.18*
210	176.40	6.72*	47.63	564.48*

megawood® panel Colonia (239 x 6mm)			р	ackage content 84 pcs.
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
158.4	133.06	2.79*	31.80	234.18*
210	176.40	3.70*	42.16	310.46*

<sup>\*</sup> These weights are approximate. Production processes may vary these weights up to 5% of the guideline.

## megawood® LIMES fencing system

megawood® bar (40 x 112 mm) package conter			ackage content 56 pcs.	
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
178.6	100.02	9.37*	11.20	524.68*

megawood® oval bar (60 x 90 mm)			p	ackage content 56 pcs.
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
178.6	78.58	10.54*	7.23	463.65*

megawood® H-shaped profile bar (38 x 30 mm)			p	ackage content 96 pcs.
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
156.6	150.34	1.82*	5.71	174.39*

megawood® H-shaped profile bar (38 x 30 mm)			р	ackage content 96 pcs.
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
178.6	171.46	2.07*	6.52	198.89*
190	182.40	2.20*	6.93	211.58*

megawood® LIMES fencing system accessories	package content in packing units
Blackened bar connectors incl. M6 x 30 mm screws, 4 pcs./pack	28 pcs.
Stainless steel panel holder, 16 pcs./pack	12 pcs.
Base plate incl. 4 pcs. M8 x 80 mm screws (galvanised)	44 pcs.
6 x 40 mm stainless steel pin, 10 pcs./pack	12 pcs.
Internal hexagonal screw for H-shaped profile bar incl. bit, stainless steel, 16 pcs./pack	1 pcs.
Stainless steel bar	1 pcs.
Insert bar for stainless steel bar	1 pcs.
Assessories set for stainless steel bar	1 pcs.

	package content	Package dimensions	Unit	Forms of delivery
Circular posts Ø 90 mm	44 pcs. per 11 pcs. side by side, per 4 pcs. stacked	1,110x440mm Length 220cm and 270cm	per 1 pc. completely foil-covered	Per bundle on untreated square support boards; bundle straps and edge protectors
Octagonal posts 90 x 90 mm	44 pcs. per 11 pcs. side by side, per 4 pcs. stacked	1,110x440mm Length 220cm and 270cm	per 1 pc. completely foil-covered	Per bundle on untreated square support boards; bundle straps and edge protectors

	Lo reneing sys			
	package content	Package dimensions	Unit	Forms of delivery
Square posts 90 x 90 mm	44 pcs. per 11 pcs. side by side, per 4 pcs. stacked	1,030x450mm Length 220cm and 270cm	per 1 pc. completely foil-covered	Per bundle on untreated square support boards; bundle straps and edge protectors
Oval posts 60 x 90 mm	44 pcs. per 11 pcs. side by side, per 4 pcs. stacked	1,030x450mm Length 220cm and 270cm	per 1 pc. completely foil-covered	Per bundle on untreated square support boards; bundle straps and edge protectors
Panel Augusta 270 x 35 x 6 mm	84 pcs. per 3 pcs. side by side, per 14 pcs. stacked	870x660mm Length 270cm	per 2 pcs. completely foil-covered	Per bundle on untreated square support boards; bundle straps and edge protectors
Panel Colonia 239 x 6 mm	84 pcs. per 4 pcs. side by side, per 3 pcs. stacked	960x250mm Length 158.4 cm and 210 cm	per 7 pcs. completely foil-covered	Per bundle on untreated square support boards; bundle straps and edge protectors
Fence set with stainless steel bar 1,810 x 1,850 mm	1 pc.	350x160mm Length 195 cm	not foil-covered	Carton; Upper & lower woods, bundle straps and edge protectors
Bar 40 x 112 mm	56 pcs. per 8 pcs. side by side, per 7 pcs. stacked	900x360mm Length 178.6cm	per 1 pc. completely foil-covered	Per bundle on untreated square support boards; bundle straps and edge protectors
Oval bar 60 x 90mm	56 pcs. per 8 pcs. side by side, per 7 pcs. stacked	830x560mm Length 178.6cm	per 2 pcs. completely foil-covered	Per bundle on untreated square support boards; bundle straps and edge protectors
H-shaped profile bar 8 UNITS 38 x 30mm	96 pcs. per 6 pcs. side by side, per 4 pcs. stacked	960x220mm Length 156.6 cm	per 4 pcs. completely foil-covered	Per bundle on untreated square support boards; bundle straps and edge protectors
H-shaped profile bar 38 x 30 mm	96 pcs. per 6 pcs. side by side, per 4 pcs. stacked	960x220mm Length 178.6 cm and 190 cm	per 4 pcs. completely foil-covered	Per bundle on untreated square support boards; bundle straps and edge protectors

### megawood® LIMES fencing system

megawood® LIMES panel Valeria (25 x 235 mm) package content 64 pc				
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
193	123.52	7.28*	29.03	465.92*

megawood® LIMES posts (100 x 100 mm)				package content 30 pcs.
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
220	66.00	19.60*	6.60	588.00*
270	81.00	24.06*	8.10	721.80*

megawood® LIMES insertion bar (6 x 34 mm)			Ī	package content 112 pcs.
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
220	246.40	0.52*	8.38	58.24*

megawood® LIMES fencing system accessories	package content in packing units
post cap round	10 pcs.

	package content	Package dimensions	Unit	Forms of delivery
LIMES Panel Valeria 25 x 235 mm	64 pcs. per 4 pcs. side by side, per 8 pcs. stacked	940x500 mm Length 193 cm	per 2 pcs. completely foil-covered	Per bundle on untreated square support boards; bundle straps and edge protectors
LIMES posts 100 x 100 mm	30 pcs. per 10 Spcs.tück side by side, per 3 pcs. stacked	1,000 x 400 mm Length 220 cm and 270 cm	per 1 pc. completely foil-covered	Per bundle on untreated square support boards; bundle straps and edge protectors
LIMES insertion bar 6 x 34 mm	112 pcs. per14 pcs. side by side, per 8 pcs. stacked	476 x 170 mm Length 220 cm	per 8 pcs. completely foil-covered	Per bundle on untreated square support boards; bundle straps and edge protectors, produce OSB board

<sup>\*</sup> These weights are approximate. Production processes may vary these weights up to 5% of the guideline.

### megawood® construction wood system

megawood® construction plank (40 x 112 mm)			package content 56 pcs.	
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
360	201.60	18.89*	22.58	1,057.59*

megawood® construction plank (40 x 145 mm)				package content 49 pcs.
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
420	205.80	28.56*	29.84	1,399.44*

megawood® circular construction wood (Ø 90 mm)				package content 44 pcs.
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
360	158.40	29.88*	14.26	1,314.72*

megawood® octagonal construction wood (90 x 90 mm)			package content 44 pcs.	
Length in cm running meter kg/pcs.			sqm/pack	kg/pack
360	158.40	29.88*	14.26	1,314.72*

megawood® square construction wood (90 x 90 mm) package				package content 44 pcs.
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
360	158.40	34.56*	14.26	1,520.64*

megawood® oval construction wood (60 x 90 mm) package content 44 pcs.				
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
360	158.40	21.24*	14.57	934.56*

megawood® construction wood Rhombus (20,5 x 81 mm)			р	ackage content 140 pcs.
Length in cm	running meter	running meter kg/pcs. sqm/pack kg/pac		
420	588.00	7.85*	47.63	1,099.5*

megawood® accessories construction wood Rhombus	package content in packing units
Clamp for construction wood Rhombus, stainless steel, 30 pcs./pack	48 pack
Clamp for construction wood Rhombus, stainless steel, blackened, 30 pcs./pack	48 pack

<sup>\*</sup> These weights are approximate. Production processes may vary these weights up to 5% of the guideline.

megawood® construction wood system

megawood® bench (69	90 x 960 mm)			package content 1 pc.
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
180	-	87.00*	-	87.00*

megawood® plant con	tainer (1,000 x 810 mm)			package content 1 pc.
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
110	-	215.00*	-	215.00*

megawood® sandpits 2	1 x hexagonal (1,200 x 30	00 mm)		package content 1 pc.
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
120	-	45.00*	-	45.00*

megawood® sandpits 2	2 x hexagonal (1,200 x 30	00 mm)		package content 1 pc.
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
210	-	75.00*	-	75.00*

megawood® sandpits 3	3 x hexagonal (2,100 x 30	00 mm)		package content 1 pc.
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
210	-	90.00*	-	90.00*

megawood® door (1,0	20 x 1,850 mm)			package content 1 pc.
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
185	-	39.60*	-	39.60*

megawood® frame (1,2	120 x 2,000 mm)			package content 1 pc.
Length in cm	running meter	kg/pcs.	sqm/pack	kg/pack
200	-	47.00*	-	47.00*

	package content	Package dimensions	Unit	Forms of delivery	
Bench 69 x 960 mm	1 pc.	690 x 240 mm Length 180 cm	not foil-covered	Per bundle on untreated square support boards; bundle straps and edge protectors	
Plant container 1,000 x 1,000 mm	1 pc.	1,100 x 1,100 mm Length 81 cm	not foil-covered		
Sandpits 1x hexagonal 2x hexagonal 3x hexagonal	1 pc.	600 x 450 mm Length 80 cm	not foil-covered	Inka pallet; carton; bundle straps and edge protectors	
Door, no filling 1,020 x 1,850 mm	1 pc.	200 x 1,020 mm Length 185 cm	not foil-covered	Per bundle on untreated square support boards; bundle straps and edge protectors	
Frame 1,120 x 2,000 mm	1 pc.	400 x 1,120 mm Length 200cm	not foil-covered		

# CERTIFICATE CRADLE TO CRADLE



Cradle to Cradle® describes a materials cycle in which the products or raw materials respectively, permanently circu-

## Within these categories, our GCC wood-based panel has been certified according to *Cradle to Cradle* \*Certified\*:

	BRONZE	SILVER	GOLD	PLATINUM
Material Health				Ø
Material Reutillzation			$\bigcirc$	
Renewable Energy			$\bigcirc$	
Water Stewardship			$\bigcirc$	
Social Fairness			Ø	

\*Version 3.1, Renewal 27 Aug 2022, with the exception of DELTA decking boards, more information on certification available at www.megawood.com/c2c

late in recurring cycles "from the cradle to the cradle". At megawood®, the wooden GCC (German Compact Composite) products pass through a technical cycle so that they can always be used for the manufacturing of new products.



PFFC.



Die HW-Zert GmbH, von PEFC Deutschland e. V. anerkannt und notifiziert, bestätigt hiermit, dass das Unternehmen

#### NOVO-TECH Trading GmbH & Co. KG

Siemensstraße 31 06449 Aschersleben

ein betriebliches Kontrollsystem unterhält, das mit den



Chain-of-Custody-Anforderungen von PEFC

Programme for the Endorsement of Forest Certification gemäß des deutschen Standards PEFC D 1003:2013 "Produktkettennachweis für Holzprodukte - Anforderungen" Deutsche Übersetzung des Internationalen PEFC- Standards PEFC ST 2002:2013 in der aktuell gültigen Fassung (siehe hierzu auch www.pefc.org) PEFC/04-31-1231 übereinstimmt.

Es wurde nachgewiesen, dass die Anforderungen bezüglich der

#### Methode der physischen Trennung

erfüllt sind und angewendet werden. Das Unternehmen hat mit der HW-Zert GmbH einen Begutachtungsvertrag abgeschlossen und wird jedes Jahr auditiert. Dieses Zertifikat berechtigt dazu, die im Geltungsbereich benannten Produkte/Produktgruppen nach der o. g. Methode als PEFC-zertifiziert und/oder PEFC kontrollierte Quellen zu verkaufen.

Art des Zertifikates: Einzelzertifikat

PEFC-Scope: Others Geltungsbereich: Produkte aus

Holz-Polymer-Werkstoffen

Registriernummer HW-Zert GmbH: HW-CoC-0354-19

15.05.2019 Datum der Ausstellung:

01.06.2019 bis 31.05.2024 Dieses Zertifikat ist gültig:

Horst Gleißker Geschäftsführer

Geschäftsführer

HW-Zert GmbH • Gallersberg 10 • 85395 Attenkirchen www.hw-zert.de • info@hw-zert.de



Deutsche Akkreditierungsstelle D-ZE-18039-01-00

Die HW-Zert ist notifiziert in Belgien, Dänemark, Deutschland, Finnland, Frankreich, Großbritannien, Irland, Italien, Kanada, Malaysia, Niederlande, Österreich, Polen, Portugal, Schweden, Schweiz, Slowakei, Slowenien sowie über PEFC international in allen Ländern ohne eigenes PEFC-System.

# ERTIFIKAT CERT



ANLAGE zum PEFC-CoC-Zertifikat der HW-Zert GmbH Nummer HW-CoC-0354-19 vom 15.05.2019

bezüglich der Chain-of-Custody-Anforderungen von PEFC für das Unternehmen

#### NOVO-TECH Trading GmbH & Co. KG

Siemensstraße 31 06449 Aschersleben

Das Zertifikat umfasst neben der o. g. Zentrale folgende Organisationsteile:

#### **ERFURT.SASSE Industry Holding GmbH & Co. KG**

Siemensstraße 29 06449 Aschersleben

#### **NOVO-TECH GmbH & Co. KG**

Siemensstraße 31 06449 Aschersleben

Dieses Zertifikat ist gültig bis:

31.05.2024

Geschäftsführer

Geschäftsführer

Akkreditierungsstelle D-ZE-18039-01-00

Deutsche

HW-Zert GmbH • Gallersberg 10 • 85395 Attenkirchen www.hw-zert.de • info@hw-zert.de



Seal of quality - exemplary\*

## QUALITÄTSGEMEINSCHAFT HOLZWERKSTOFFE E.V.

# CERTIFICATE

2020 – 14-1 for WPC-decking profiles

The decking profile of type

megawood CLASSIC

kind of profile	solid		based on	PE
thickness/width	21 x 145 mm	~	content of natural fibre	W>55, R<20

of the manufacturer

NOVO-TECH GmbH & Co. KG, 06449 Aschersleben, Germany

confirms with his testing results of the external supervision, done by the independent and certified institute

Entwicklungs- und Prüflabor Holztechnologie GmbH Zellescher Weg 24, 01217 Dresden, Germany

and the initial inspection of factory and the supervision of factory production control, done by the Qualitätsgemeinschaft Holzwerkstoffe e. V., Schumannstr. 9, 10117 Berlin (Germany) the requirements according the quality and testing criteria for decking profiles of Wood-Polymer-Composites (dated 1st March 2017).

The manufacturer is entitled to use the quality label



megawood - QG/2010/Z14, PE

Wood-Polymer-Composites of certified production

- Wood from sustainable forestry
- Rice husk from controlled farming
- Pure industrial Polymer

Validity of the certificate is 12 months and so long as the quality criteria are not changed and the fulfilment of these criteria by the manufacturer is given.

Berlin, 25 September 2020

Anemon Strohmeyer General Manager

Qualitätsgemeinschaft Holzwerkstoffe e.V. • Schumannstr.9 • 10117 Berlin • Germany Telefon +49 (0) 30 28 09 12 50 • info@gg-holzwerkstoffe.de

Certificate solid boards - exemplary\*







# PRÜFUNGSZEUGNIS

#### CT-13-01-07-01

Produkt: Megawood Massivdiele, grau

Firma: NOVO-TECH GmbH & Co. KG

Siemensstraße 31 06449 Aschersleben

Auftrag: Bestimmung des Migrationsverhaltens von Schwermetallen nach

**DIN EN 71-3** 

Prüfmethodik: Extraktion mit salzsaurem Wasser

Chemische Analyse: MP-AES (Mikrowellenplasma induzierte

Atomemissionsspektrometrie)

Prüfbericht: 152013/1 vom 20. Dezember 2012

Prüfergebnis: Das Produkt "Megawood Massivdiele, grau" erfüllt sicher die

nach DIN EN 71-3 gestellten Anforderungen hinsichtlich der Konzentrationen eluierbarer Schwermetalle (As, Sb, Ba, Cd, Cr,

Pb, Hg und Se).

Dresden, 07. Januar 2013

Leiter des Prütiaboratoriums



OS - Walls CA verantwortlicher Bearbeiter

# **TEST REPORT**

Determination of the anti-slip property

PRÜFEN : UBERWACHEN : ZERTIFIZIEREN

### **BAUSTOFFPRÜFSTELLE Wismar GmbH**



NOVO - TECH GmbH & Co. KG

Siemensstraße 31 GER-06449 Aschersleben

> Wismar, 25.04.2017(V) our signature: Sü/St./Vo.

Test report no.:	0595/17-V
Customer:	NOVO - TECH GmbH
Subject matter:	Testing accordance  - Determination of the anti-slip properties - wet loaded barefoot areas according to DIN 51097 - 1992:11  - Determination of the anti-slip property - Workrooms and fields of activities with slip danger, walking method - Ramp test according to DIN 51130:2014-02  - Determination of the displacement space to DIN 51130:2014-02
Subject date:	10.04.2017
Samples received:	12.04.2017
Test date:	13.04.2017
Name of the product:	megawood deck board Classic Jumbo solid - grooved Dimensions I/w/h [cm]: 1000 x 242 x 21
Number of samples:	2,5 tiles
Origin:	as customer
Sampling:	The samples were provided by the customer.

The test report comprises 3 pages.

This test report replaces the test report-No. 0595/17 of 18.04.2017.

The test report is valid for 5 years, unless there are conditions that may change the surface condition.

Evidential samples shall only be stored for 2 months.

Durch the CARRO Nati Oth FM 100EC 1702 extractories Professioninum Dis Assertiming of both to the militarization and the Carro State of the Carro

Annual Lubeche Birate 107 23965 Warmer C. FOR +45 (6)344 76 20 00 11 45 45 (6)341 76 20 00 11 46 46 (6)341 76 20 70 11 46 (6)341 76 20 11 46 (6)341 76 20 11 46 (6)341 76 (6)341 76 (6)341 76 (7)341



# **TEST REPORT**

## Determination of the anti-slip propertyt

Baustoffprüfstelle Wismar GmbH Lübsche Straße 109, 23966 Wismar Tel.: 0 38 41 / 76 23 06; FAX: 0 38 41 / 76 30 78

of the test report no.; 0595/17-V

Page: 2

Determination of the anti-slip property according to DIN 51130:2014-02 "Determination of the anti-slip property - Workrooms and fields of activities with slip danger - Walking method

- Ramp test" and

<u>Determination of the anti-slip properties according to DIN 51097:1992-11 "Determination of the anti-slip properties - wet-loaded barefoot areas - walk method - ramp test"</u>

#### Descrition of the panel:

colour/layout: grey

surface:

trapezoid corrugated

#### Preparation of the test cover:

A test cover, size  $100 \times 60$  cm was produced by laying on a self-supporting, non-warping panel.

The width of a joint amounted to 3 mm.

The cover was cleaned with a dry cloth before the start of the test.

#### Mean angle of inclination:

Test no.	Corrected overall angle of acceptance DIN 51 130 increased skid risk [°]	angle of inclination DIN 51097 wet-loaded barefoot areas [°] 42,3	
1	29,4		
2	29,1	43,0	
3	29,5	42,0	
4	28,5	42,9	
5	27,4	41,8	
6	27,6	42,8	
7	-	42,4	
8	•	41,2	
Mean value	28,6	42	
Mean angle of inclination for assessement group shown below:	> 27 - 35	> 24	

#### Assessment group:

In accordance with the test results obtained pursuant to the guidelines of DIN 51130 the tiles are to be classified in assessment group  $\,$  R 12.

In accordance with the test result obtained pursuant to the guidelines of DIN 51097 the natural stone tiles are to be classified in assessment group **C**.

# TEST REPORT

## Determination of the anti-slip property

Baustoffprüfstelle Wismar GmbH Lübsche Straße 109, 23966 Wismar Tel.: 0 38 41 / 76 23 06; FAX: 0 38 41 / 76 30 78

Page: 3 of the test report no.: 0595/17-V

 Determination of the displacement space to DIN 51130:2004-06 "Determination of the anti-slip properties - working rooms and working areas with an increased skid risk - walk test - inclined plane"

#### Mean angle of inclination:

Test no.	Surface-related least volume of the displacement space	
1	8,2	
2	7,5	
3	8,1	
4	8,1	
5	7,7	
Mean value	8,0	

Dipl.-Ing. (FH) Ch. Schümer Official in Charge

( 2

Dipl.-Ing E. Stoige Director of the Test Office

# **OVERVIEW**

## anti-slip properties and fire behaviour

# Summary of the anti-slip properties and fire behaviour of the megawood® barefoot boards

	Anti-slip pursuant to standard DIN 51130 (R classes)	Fire behaviour** pursuant to DIN 13501-1	
Board DELTA* 21 x 145 mm	conforms with R 12	normal flammability Dfl-s1	
Board CLASSIC* 21 x 145 mm	conforms with R 12	normal flammability Dfl-s1	
Board CLASSIC Jumbo* 21 x 242 mm	conforms with R 12	normal flammability Dfl-s1	
Board CLASSIC Varia* 21 x 195 mm	conforms with R 10	flame retardant Cfl-s1	
Board SIGNUM* 21x145mm	conforms with R 10	normal flammability Dfl-s1	
Board SIGNUM* 21 x 242 mm	conforms with R 10	normal flammability Dfl-s1	
Board PREMIUM* 21x145 mm	conforms with R 11	normal flammability Dfl-s1	
Board Jumbo PREMIUM* 21x242mm	conforms with R 11	normal flammability Dfl-s1	
Board PREMIUM PLUS* 21 x 145 mm	conforms with R 11	flame retardant Cfl-s1	
Board Jumbo PREMIUM PLUS* 21 x 242 mm	conforms with R 11	flame retardant Cfl-s1	
Board DYNUM* 21 x 242 mm	conforms with R 10	flame retardant Cfl-s1; B <sub>ROOF</sub> (t1)	
Board DYNUM* 25 x 293 mm	conforms with R 10	flame retardant Cfl-s1	

<sup>\*</sup> All of the test reports are availably by request.

<sup>\*\*</sup> It is stipulated in the federal state building regulations that floor coverings in required stairwells, corridors and therefore also balconies and pergolas that serve as primary or secondary escape routes are to be made of hardly inflammable building materials (fire class Cfl-S1) as a minimum.

The hardly inflammable boards can be used as floor coverings in primary and secondary escape routes in building regulation terms! The respective fire prevention concepts are to be inspected.

#### Classification of fire behavior



#### Klassifizierungsbericht

Classification report

Nr.: 2714232

Entwicklungs- und Prüflabor Holztechnologie GmbH Zellescher Weg 24 01217 Dresden

Tel.: +49 351 4662 0 Fax: +49 351 4662 211 info@eph-dresden.de www.eph-dresden.de

#### Klassifizierung zum Brandverhalten gemäß DIN EN 13501-1:2010

Reaction to fire classification according to DIN EN 13501-1:2010

Auftraggeber (AG): NOVO-TECH GmbH & Co. KG

Client: Siemensstraße 31

06449 Aschersleben

Hersteller: siehe Auftraggeber

Manufacturer: cf. client

Produktname: megawood® Classic Barfußdiele, WPC-Terrassendiele massiv; 21 mm
megawood® Classic barefoot board, massive WPC decking board; 21 mm

Bodenbelag für den Außenbereich / Floor covering for exterior use

Klassifikation: D<sub>ff</sub>-s1

Geltungsdauer: k. A. Validity: n/s

Ausgabe-Nr.: 1. Ausfertigung / Original

Issue-No.: Original

Datum der Ausgabe: 26.06.2014

Date of issue:

Auftragnehmer (AN): Entwicklungs- und Prüflabor Holztechnologie GmbH - EPH

Contractor: Laborbereich Oberflächenprüfung

Development and Examination Laboratory for Wood Technology Ltd. - EPH

Laboratory Surface Testing

Notifizierte Stelle – Nr.: 0766

Notified body - No.:

Verantw. Bearbeiter:

Engineer in charge: Dipl.-Ing. Ch. Kniest

1.

Dr. - Ing. R. Emmler

Leiter Laborbereich Oberflächenprüfung / Head of Laboratory Surface Testing

Der Klassifizierungsbericht umfasst 4 Seiten. Jede auszugsweise Vervielfältigung bedarf der schriftlichen Genehmigung des EPH. Die Prüfergebnisse beziehen sich ausschließlich auf die geprüften Materialien. Dieser Bericht ist zweisprachig. Im Zweifel gilt der deutsche Wortlaut.

The classification report contains 4 pages. Any duplication, even in part, requires written permission of EPH. These test results are exclusively related to the tested material. This report has been issued billingually. In case of doubt, the German version is valid.

Geschäftsführer Dr., Ing. Bernd Devantier Amtsgericht Dresden HRB 8072 USt. IdNr. DE 21 60 77 44 6 Commersbank AG SWIFT: DRES DE FF 850 IBAN: DE 13 8508 0000 0400 2982 00





#### Classification of fire behavior



Branch office Erwitte • Auf den Thränen 2 • D-59597 Erwitte • Tel. (0 29 43 ) 8 97-0 • Fax (0 29 43) 8 97-33 • email: erwitte@mpanrw.de

#### Report of the classification of the reaction to fire behaviour

No 230010960-2 of 1 June 2017

**English Version** 

Customer: NOVO-TECH GmbH & Co. KG

Siemensstraße 31

06449 Aschersleben

Reaction to fire classification according to DIN EN 13501-1 Order:

2 March 2017 Date of order:

Designation of the building product to be classified:

Decking board flooring referred to as "Megawood Litum Steinholzplatte"

This report determines the classification of the above-mentioned building product in accordance with the method specified in DIN EN 13501-1.

Publishing and copying of classification reports without permission of MPA NRW is only allowed without any changes of the content and the form of the reports.

This classification report consists of 3 pages.

#### Classification of fire behavior



Classification Report No. 230010960-2 of 1 June 2017

Page 2 of 3

#### 1 Description of the building product

The building product designated "Megawood Litum Steinholzplatte" is decking board flooring with the following structure:

The decking boards are about 20 mm thick and consist of a wood-polymer material with stone granules. They have a metre weight of approx. 6.1–7.9 kg/metre. The surface is nidged on one side and the underside is smooth. The decking boards must be laid on Powolit construction beams.

#### 2 Test reports and test results on which the classification is based

#### 2.1 Test reports

Name of laboratory	Customer	Test report number	Test method
MPA NRW	NOVO-TECH GmbH & Co. KG	230010960-1 of 1 June 2017	EN ISO 9239-1 EN ISO 11925-2 (15 s flame resistance)

#### 2.2 Test results

69 07 MINON HOVE A TOX		Number of	Test results	
Test method	Parameter	tests	Mean values	Requirement fulfilled
DIN EN ISO 11925 15 s B flame resistance	Flame propagation ≤ 150 mm	6	-	Yes
DIN EN ISO 9239-1 (kW/n	Critical heat flow (kW/m²)	3	5.5	
	Smoke (%xmin)	3	191	

#### Classification of fire behavior



Classification Report No. 230010960-2 of 1June 2017

Page 3 of 3

#### 3 Classification and direct field of application

#### 3.1 Reference

The classification was carried out in conformity with clauses 12 and 14.2 of the standard DIN EN 13501-1:2010.

#### 3.2 Classification

The classification assigned to the material with regard to its reaction to fire: Cn

The additional classification with regard to smoke production: s1

This results in the following reaction to fire classification of the flooring:

Reaction to fire	Smoke production		
Cfl	s1	i.e.	C <sub>fl</sub> - s1

#### 3.3 Field of application of the product

The classification is valid solely for the building product described in Section 1 when used as flooring, laid horizontally – glued or not glued – on a base in Euro classes A1 or A2 in accordance with DIN EN 13501-1 with a raw density of at least 1,350 kg/m³ and a thickness of at least 6 mm.

#### 4 Restrictions

This test report does not replace any type approval or certification of the product. This test report written in English language is issued additionally to the report written in German language with the same report number. In case of doubt the German version is solely valid.

Erwitte, 1 June 2017

Dipl.-Ing. Schreiner (Deputy Head of the testing body) (Dipl.-Ing. Olaf Rickert)

Date of issue of this English version: 2 December 2019





#### INTERACTIVELY EXPERIENCEMEGAWOOD®

You can construct a a virtual megawood® deck in front of your house with the megaplaner App for iOS and Android. In order to do so, simply enter the dimensions of your deck and receive your individual construction plan!

View your new megawood® deck from all directions: From the subconstruction to the barefootboard. Simply position this marker page at the point where you would like to build your deck, scan it with your Smartphone or tablet and experience your new deck live and in 3D.

YOUR DEALER





